

SWISSMDF P213 SM PAINTING GRADE

✓ CARB II / TSCA Title VI ✓ E1-D2020 (ChemVerbotsV) ✓ E1

Application

SWISSMDF P213 SM PAINTING GRADE with its special open impregnation offers a homogenous, silk-matt surface for lacquering. Suitable for use for non-load-bearing furniture, object, and interior fittings.



Technical class

Medium density fibreboard (MDF acc. EN 622-5) as non-structural components in dry conditions.

Technical data

Coating thickness	0.1	mm	
-------------------	-----	----	--

Depend on coating of surface / edges.

Tolerances

Thickness	± 0.3	mm	EN 324-1
Flatness	≤ 2	mm/m	EN 14323

Ecological information (SIA 493)

Renewable energy > 90% | Wood 80-85% | UF adhesive 9-13% | Emulsion < 1% | Swiss conifer wood from thinning and sawmill residue | No post-consumer recycled content | No chlorides and no biocides | Thermally recyclable.