

SWISS KRONO LLC, Y.Mudroho St., 62,  
80400 Kamianka-Buska, Lviv Region, Ukraine

### Technical Specifications

For front plates (glossy boards) production we use HPL laminate. The surface properties of front plate (glossy board) are according to EN 438-3: 2005 . We use VG type HPL for front plate (glossy board) production. On the back side of plate is the white color balanced material impregnated with water resistant additives is used from the reverse side of the boards.

Characteristic	Method	Value	
<b>Gloss level</b>	ISO 2813 (60°)	≥110°	
<b>Resistance to surface wear</b>	EN 438-2.10	Initial Point	≥50
		Wear Value	≥150
<b>Resistance to scratching</b>	EN 438-2.25	2	
<b>Resistance to dry heat (180°C)</b>	EN 438-2.16	3*	
<b>Resistance to wet heat (100 °C)</b>	EN 12721	3*	
<b>Resistance to staining</b>	EN 438-2.26	5*	
<b>Resistance to cigarette burns</b>	EN 438-2.30	3*	

SWISS KRONO LLC  
Y.Mudrogo St., 62, 80400 Kamianka-Buska,  
Lviv Region, Ukraine  
T +38 089 226 86 00

ua.sekretariat@swisskrono.com  
swisskrono.ua

Registered in Ukraine No. 31147999, VAT No. 311479913208, JSC «CREDIT AGRICOLE» IBAN – UA67 300614 0000026001500249700  
JSC «KREDOBANK» », SWIFT: WUCBUA2X IBAN – UA38 325365 0000002600101778646  
JSC «RAIFFEISEN BANK AVAL» IBAN – UA53 380805 0000000026009528945  
JSC «ALFA-BANK» IBAN – UA36 300346 0000026008015596501