REACTION TO FIRE CLASSIFICATION REPORT IN ACCORDANCE WITH PN-EN 13501-1+A1:2010

Contract no. 01154/17/Z00NZP

Sponsor:	SWISS KRONO Sp. z o.o. ul. Serbska 56 68-200 Żary				
Prepared by:	Building Research Institute; 1, Filtrowa str. 00-611 Warszawa, Poland				
Product name:	SWISS KRONO Worktop				
Classification report №:	01154.2/17/Z00NZP-E				
Issue number:	Copy No 2 (English Version of 2558.4/16/Z00NZP)				
Date of issue:	2017-06-22				

This classification report consists of 4 pages and may only be used or reproduced in its entirety.

1. Introduction

This classification report defines the classification assigned to the **SWISS KRONO Worktop** in accordance with the procedures given in PN-EN 13501-1+A1:2010.

2. Details of classified product

2.1 General

Product is defined as worktop.

2.2 Product description

The product, is described below.

SWISS KRONO Worktop is made from partical board: of thickness 28 mm and density 630 kg/m³ or of thickness 38 mm and density 600 kg/m³. Partical boards are covered from one side by CPI-laminate of thickness 0,5-0,8 mm or by HPL laminate of thickness 0,6-0,8 mm. Rear side is covered by paper.

Product is produced by SWISS KRONO Sp. z o.o.

3. Test reports & test results in support of classification

3.1 Test reports

Name of laboratory	Name of sponsor	Test report no.	Test method	
Fire Research Department SWI	SWISS KRONO	LP-02270/23-57/09	PN-EN ISO 11925-2: 2004	
Building Research Institute	g Research Sp. z o.o.	LP-02270/34-51/09	PN-EN 13823: 2004	

3.2 Test results

			Results	
Test method	Parameter	Number of tests	Continuous parameter – mean (m)	Compliance with parameters
PN-EN ISO 11925-2: 2004 Surface and edge exposure. Exposure time 30 s.	F _s ≤150 mm	12	(-)	Y
	Flaming Droplets/particles		(-)	N
PN-EN 13823: 2004 Plywood protected by 25% aqueous solution of fire protection agent named BURNBLOCK.	FIGRA _{0,2MJ}	3	484,8	(-)
	FIGRA _{0,4MJ}		452,6	(-)
	LFS < edge		(-)	Υ
	THR _{600s} [MJ]		29,1	(-)
	SMOGRA [m ² /s ²]		10,8	(-)
	TSP _{600s} [m ²]		68,9	(-)
	Flaming Droplets/particles		(-)	N

(-): not applicable

Y: Yes N: No

4 Classification and field of application

4.1 Reference of classification

This classification has been carried out in accordance with PN - EN 13501-1+A1:2010.

4.2 Classification

The product, SWISS KRONO Worktop, in relation to its reaction to fire behaviour is classified:

D

The additional classification in relation to smoke production is:

s2

The additional classification in relation to flaming droplets/particles is:

d0

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation products is:

Fire behaviour		Smoke production		Flaming droplets		
D	-	s	2	,	d	0

i.e.: D-s2,d0

Reaction to fire classification: D-s2,d0

4.3 Field of application

This classification is valid for the product described in clause 2.2 of this classification report.

5 Limitations

This classification given remains valid as long as:

- Test method remains unchanged.
- Product standard or technical approval remains unchanged.
- Constructional or material modifications do not exceed limits of the field of application defined in 4.3.

This classification report has been issued in three copies (2 for Sponsor, 1 for archive of Fire Research Department of Building Research Institute). Additional signed copies can be issued by Fire Research Department of ITB on the request of the report's owner only.

In case of doubt the polish language version (02558.4/16/Z00NZP) is the only basis for interpretation.

VALID ONLY WITH PROOF OF PURCHASE

This classification document does not represent type approval or certification of the product.

SIGNED

Andrzej Kolbrecki Ph.D. Eng

Kollered

APPROVED

Head of Fire Research Department

Paweł Sulik Ph.D Civil Ing.