

Parameter	Unit of measure	Requirements GOST 52078-2003	Tests according to the standards
Specific surface resistance to abrasion rotations	rotations	≥65	GOST 27820
Specific resistance to stain formation <ul style="list-style-type: none"> • distilled water • ethyl alcohol 96% • acetic acid 10% • coffee (12gr per 100cm³) 		Any surface appearance changes are not permitted	GOST 27627
Specific resistance of the outside layer to tear off, normal	mPa	≥0.8	GOST 23234
Warpage of double-side laminated melamine faced particle boards	mm	≤1.2	GOST 24053